

# **SURFACE FINISH CHARTS**

## **Surface Finishing:**

### **Mechanical Polishing and Electro Polishing**

#### **Machining and mechanical polishing**

Mechanical polishing or machining leaves numerous surface scratches which cause areas of differing electrical potential due to surface stresses. An electro polished surface is essentially balanced.

Local corrosive cells cannot be set up, because the local galvanic differences caused by polishing stresses in the stainless surface have been eliminated.

The most effective method of eliminating burrs, folds, inclusions and other abnormalities is through Electro polishing. This electrolytic process, the opposite of the plating process, is designed to remove metal without smearing or folding. Peaks are dissolved more quickly than valleys as a result of the greater concentration of current over the protuberances. This action produces a smoothing and rounding of the surface profile. Due to the rounded profile, electro polished surfaces are far easier to clean than surfaces mechanically polished alone.

#### **Surface Finish**

Measuring and specifying surface finish has, until recently, been left to a varying amount of speculation. The number of different standards being used by different equipment manufacturer has created a great deal of confusion and misunderstanding throughout the industry.

Increasingly stringent specifications are now being demanded for the surface finish on all items of process equipment in the pharmaceutical and biotechnology industries and many suppliers of valves and pipe work are now quantifying the surface roughness of their product.

The specification of grit reference cannot be equated to a consistent surface finish. Variables affecting the resultant finish are grit size, tool load, condition of tool, feed rate, traverse rate condition of metal to be polished and lubricant used, if any.

For precise and consistent results, surface finish should be specified in a range or maximum level of roughness average (Ra). This is normally expressed in micrometers (Microns) or micro inches.

Micron or micro inch values expressing surface finish as roughness average (Ra) are interchangeable with those values identified as (CLA) centerline average or arithmetic average. Measured values expressed as (RMS) root mean square will read approximately eleven percent higher than values expressed in Ra. (Micro inches x 1.11 = RMS). For surface roughness measurements, BBS-Systems utilizes a surface measurement instrument. Surface finish can then be described by using the roughness average (Ra) parameter. The Ra value is defined as the average value of the departures from its centerline through a prescribed sampling length.

The increasing purity requirements in the pharmaceutical and bio-technology industries require surfaces in contact with the product to have finishes that meet BPE standards. With the advent of ASME/BPE, the Pharmaceutical and biotechnology industries finally have a standard that can be universally applied.

#### **Some values of surface finish**

- Grit: Measures the number of scratches per linear inch of abrasive pad. Higher numbers indicate a smoother surface

Standard Grit (reference only)	Ra $\hat{A}\mu\text{in}$	Ra $\hat{A}\mu\text{m}$	RMS $\hat{A}\mu\text{in}$	RMS $\hat{A}\mu\text{m}$
150	27 - 32	0.68 - 0.80	30 - 35	0.76 - 0.89
180	16 - 23	0.46 - 0.58	20 - 25	0.51 - 0.64
240	14 - 18	0.34 - 0.46	15 - 20	0.38 - 0.51
320	8 - 10	0.21 - 0.25	9 - 11	0.23 - 0.28

- RMS: defined as Root Mean Square roughness, this method measures a sample for peaks and valleys. Lower numbers indicate a smoother finish
- Ra: Known as the arithmetic mean, this measurement represents the average of all peaks and valleys. Lower numbers indicate a smooth finish

### Electro polishing

Electro polishing is a process combining electric current and chemicals to remove surface material; it is the most effective method of removing burr, folds, inclusion and other abnormalities. Peaks are removed quicker than valleys because of the concentration of current on the peaks. This process leaves the surface extremely smooth and is far easier to clean by reducing the total area required to be sterilized. This electrolytic process is frequently specified because of the broad range of inherent benefits over mechanical polishing alone.

The inherent benefits of Electro polishing subsequent to mechanical polishing are as follows:

- Superior surfaces for cleaning and sterilization.
- Resultant passivated surfaces enhance corrosion resistance.
- High luster reflective appearance.
- Elimination of smeared or torn surfaces caused by abrasive finishing
- Removal of inclusions and entrapped contaminants such as lubricants and grit particles.
- Increased corrosion resistance
- Cleaner surface of the wet contact areas
- Removal of surface occlusions
- Reduce surface friction

Electro polishing also greatly reduces the total surface area to be cleaned and sterilized.

Surface Finish Comparison				
RMS (Micro-inch)	RMS (Micron)	Ra (Micro-inch)	Ra (Micron)	Grit Finish
160	4.06	142	3.61	36
98	2.49	87	2.21	60
80	2.03	71	1.80	80
58	1.47	52	1.32	120
47	1.20	42	1.06	150
47	1.20	42 Before Bead Blast	1.06	USDA Bead Blast

34	0.86	30	0.76	180
21	0.53	19	0.48	220
17	0.43	15	0.38	240
14	0.36	12	0.30	320
10	0.25	9	0.23	400
5	0.13	4 (+/-)	0.10	Mirror